

COLTOU

BI-COMPONENT GLUE METHYLMETHACRYLATE





7 good reasons for using COLTOU

- 1. Universal: adheres to all materials: metal, glass, plastic, PVC Plexiglas, concrete, natural stone, wood, rubber
- Rapid: setting time less than 2 min.
- 3. High tensile strength: 3500N/cm².
- 4. High **temperature** resistance up to 200°C.
- 5. Resistant to impacts and vibrations.
- 6. Easy to use: does not require gun application. The mix nozzle gives a perfect blend of the 2 components.
- 7. Aesthetic: translucent blending.

Particularly suitable for use in



Public buildings





For assembling on various supports: steel, stainless steel, copper, brass, titanium, ferrite, glass, plastic, Plexiglas, concrete, stone, Aluminium... Can replace the riveting.

Characteristics

Composition: bi-component methylmethacrylate

Density: 1.02

Use at: +5°C to +35°C; polymerization faster with

Resistance to temperature: -40°C to +180°C up to 200°C max.

Setting speed: <2mn

Hardening speed between 2 and 7 mn Volume: 2x12,5ml

For more information, see MSDS.



Instructions for use

Clean the parts to be glued.

Make sure that the 2 components squeeze out equally and then fix on the mixer tip.

Squeezes out the necessary quantity.

If you stop activating the pistol for more than 1 minute, change the tip and begin again.

When the operation is finished, remove the tip and clean cartridge end with a rag taking care not to mix the 2 components and not to create hardened particles in this end which could block the mixer tip.

Use without gun application.

GB026072015/4

ALUCOL: a use cold adhesive strip for watertightness

This datasheet supersedes previous documents. The information contained in these data sheets is based on our present knowledge and experience and is given as indication only. Under no circumstances does it engage our responsibility in the event of misuse of our products. Non-contractual photos and images.



7d'Armor