DECOFRINE VG







- 1. DECOFRINE VG is for deferred form removal, ready to use.
- 2. To obtain a perfect finish of the surfaces. After removal, does not stain.
- 3. Is applied by simple pulverizing. Totally insoluble in the water
- 4. Eliminates the **bond** of cements, concretes, plasters.
- 5. Good weather resistance.
- 6. DECOFRINE VG is compatible with all the hydraulic binders and guarantees a high quality facing.
- 7. Its formulation from oil and vegetable esters is free of solvents of petrol origin.



Particularly suitable for use in

Classification Synad	Products for turning out
Environment	****
Health	****
Fire security	****
Very good ♦♦♦♦	very bad 🍑

For the turning out of metallic, plasticized or wood formwork. Use for manufacturing paving stones, fence panels con-

crete pickets. For protection equipment from projections of cement or plaster as well as any metallic surfaces against corrosion. Particularly adapted for the new form panels, with stands steaming up to 40 °C and is used on most of the casings for the architectural concretes and in prefabrication.

Characteristics	Instructions for use
Composition: Vegetable pure oil	Surface preparation: The surface must be clean, dry and free of dust.
Appearance: amber liquid Density: 0.89 +- 0.02 Viscosity at 20°C: 13.4 seconds with the fraction	Product preparation: Ready to use, spray or use a cloth in a thin and uniform laver.
Ford N°4 at 20 °C. Flash point: > 100 °C.	Application: Apply 1 thin layer, evenly and without excess. On horizontal sur- faces, eliminate the surplus with a rubber scraper.
Ultimate biodegradability: 65 % in 28 days accord- ing to NF standard IN ISO 9408 - OECD 301 F. Consumption according to casings, 1 I for a sur-	<u>Finishing</u> : Does not attack the qualities of concretes and mortars and these can be painted without problems. Does not modify the bond key of fillers, plasters, roughcasts and paints.
face of 30 - 50 m ² . Applying temperatures max: + 5 °C to + 40 C	Clean tools with VG KLEAN.
Cold resistance: the product freezes, thickens with the cold without losing its properties (Up to -5 °C).	PARTICULAR PRECAUTIONS AND SAFETY
For more information, see MSDS.	Avoid product surplus (phenomenon of chalking). Do not apply to frozen or heated casing. Storage: 2 years in closed original packaging, shielded from very hot tempera- tures.

GB22112022/1

will be limited exclusively to product replacement or refund of defected quantities without other compensation. Ned with the nature, prescriptions as well as the product use not respected the instructions of the technical datas

quality. In case of defect are excluded from the war

utmost care in preparin the order and the product resulting from storage, handling, transport or use a

7 d'Armor® ti Defects and o

7 + VG KLEAN : Plant-based degreaser

This datasheet supersedes previous documents. The information contained in these data sheets is based on our present knowledge and experience and is given as indication only. Under no circumstances does it engage our responsibility in the event of misuse of our products. Non contractual photos and images.



Tél 02 97 54 50 00 Www.7darmor.fr

